



# LOCTITE® 4013™

February 2010

## PRODUCT DESCRIPTION

LOCTITE® 4013™ provides the following product characteristics:

<b>Technology</b>	Cyanoacrylate
Appearance (uncured)	Transparent, colorless to slightly yellow liquid <sup>LMS</sup>
Components	One part - requires no mixing
Viscosity	Medium
<b>Cure</b>	Humidity
<b>Application</b>	Bonding
Key Substrates	Plastics and Metals

LOCTITE® 4013™ is designed to provide fast room temperature fixturing. Suitable for use in the assembly of **disposable medical devices**.

### ISO-10993

An ISO 10993 Test Protocol is an integral part of the Quality Program for LOCTITE® 4013™. LOCTITE® 4013™ has been qualified to Henkel's ISO 10993 Protocol as a means to assist in the selection of products for use in the medical device industry. Certificates of Compliance are available on Henkel's website or through the Henkel Quality Department.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.1
Viscosity, Brookfield - LVF, 25 °C, mPa·s (cP):	
Spindle 2, speed 30 rpm	400 to 800 <sup>LMS</sup>
Flash Point - See MSDS	

## TYPICAL CURING PERFORMANCE

Under normal conditions, the atmospheric moisture initiates the curing process. Although full functional strength is developed in a relatively short time, curing continues for at least 24 hours before full chemical/solvent resistance is developed.

### Cure Speed vs. Substrate

The rate of cure will depend on the substrate used.

Fixture Time, seconds:	
PVC to PVC	20 to 25
ABS to ABS	5 to 10
Polycarbonate to Polycarbonate	10
Polyurethane to Polyurethane	6 to 8
G-10 Epoxy to G-10 Epoxy	15 to 20
Stainless steel to PVC	5 to 10
Stainless steel to ABS	5 to 8
Stainless steel to Polycarbonate	5 to 8
Stainless steel to Polyurethane	15 to 20
Stainless steel to G-10 Epoxy	6 to 10

### Cure Speed vs. Bond Gap & Humidity

The rate of cure will depend on the bondline gap. Thin bond lines result in high cure speeds, increasing the bond gap will decrease the rate of cure. The rate of cure is also influenced by the ambient relative humidity; the higher the relative humidity, the greater the cure speed.

### Cure Speed vs. Activator

Where cure speed is unacceptably long due to large gaps, applying activator to the surface will improve cure speed. However, this can reduce ultimate strength of the bond and therefore testing is recommended to confirm effect.

## TYPICAL PROPERTIES OF CURED MATERIAL

After 24 hours @ 22 °C

### Physical Properties:

Tensile Strength, ISO 527-3	N/mm <sup>2</sup>	28
	(psi)	(4,000)
Elongation, ISO 527-2, %		2
Shore Hardness, ISO 868		65

## TYPICAL PERFORMANCE OF CURED MATERIAL

### Adhesive Properties

Cured for 24 hours @ 22 °C

Lap Shear Strength, ISO 4587:

Steel (grit blasted)	N/mm <sup>2</sup>	≥12 <sup>LMS</sup>
	(psi)	(≥1,740)
PVC to PVC	N/mm <sup>2</sup>	>5
	(psi)	(>725)
ABS to ABS	N/mm <sup>2</sup>	>4
	(psi)	(>580)
Polycarbonate to Polycarbonate	N/mm <sup>2</sup>	>7
	(psi)	(>1,015)
Stainless steel to ABS	N/mm <sup>2</sup>	>5
	(psi)	(>725)
Stainless steel to PVC	N/mm <sup>2</sup>	>4
	(psi)	(>580)
Stainless steel to Polycarbonate	N/mm <sup>2</sup>	>4
	(psi)	(>580)
Stainless steel to Polyurethane	N/mm <sup>2</sup>	1.5
	(psi)	(220)

Cured for 10 seconds @ 22 °C

Tensile Strength, ISO 6922:

Buna-N	N/mm <sup>2</sup>	≥6.9
	(psi)	(≥1,000)

## TYPICAL ENVIRONMENTAL RESISTANCE

### Humidity Resistance

38°C - 85% Relative Humidity

#### Adhesive Properties

Lap Shear Strength, ISO 4587, N/mm<sup>2</sup> :

Substrates	1*	2*	3*	4*
PVC to PVC	>5	>4.5	>5	>5
ABS to ABS	>4	>4	>4	>3
Polycarbonate to polycarbonate	>7	>4	>5	>3.5
Stainless Steel to PVC	>5	>5.5	>5.5	>4
Stainless Steel to ABS	>4	>4	>4	>3.5
Stainless Steel to Polycarbonate	>4	>4.5	>2.5	>2
Stainless Steel to Polyurethane	1.5	1.5	1.5	1.1

\* 1 - Control

\* 2 - Aged 1 Week

\* 3 - Aged 4 weeks

\* 4 - Aged 8 weeks

### Effects of Sterilization

In general, products similar in composition to LOCTITE® 4013™ subjected to standard sterilization methods, such as EtO and Gamma Radiation (25 to 50 kiloGrays cumulative) show excellent bond strength retention. LOCTITE® 4013™ maintains bond strength after 1 cycle of steam autoclave. It is recommended that customers test specific parts after subjecting them to the preferred sterilization method. Consult with Loctite® for a product recommendation if your device will see more than 3 sterilization cycles.

### GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials**

**For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).**

#### Directions for use:

1. For best performance bond surfaces should be clean and free from grease.
2. This product performs best in thin bond gaps (0.05 mm).
3. Excess adhesive can be dissolved with Loctite cleanup solvents, nitromethane or acetone.

#### Loctite Material Specification<sup>LMS</sup>

LMS dated November 27, 2002. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

### Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

### Conversions

(°C x 1.8) + 32 = °F

kV/mm x 25.4 = V/mil

mm / 25.4 = inches

µm / 25.4 = mil

N x 0.225 = lb

N/mm x 5.71 = lb/in

N/mm<sup>2</sup> x 145 = psi

MPa x 145 = psi

N·m x 8.851 = lb·in

N·m x 0.738 = lb·ft

N·mm x 0.142 = oz·in

mPa·s = cP

### Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.2