

LOCTITE® LOCTITE® Contact Adhesive

December 2006

PRODUCT DESCRIPTION

LOCTITE® Contact Adhesive provides the following product characteristics:

Technology	Solvent based
Chemical Type	Neoprene rubber
Appearance	Yellow liquid ^{LMS}
Cure	Air dry
Application	Bonding-maintenance
Specific Benefit	<ul style="list-style-type: none"> • Repositionable after initial assembly • Fast, high strength bonds • Waterproof

LOCTITE® Contact Adhesive is a contact cement used for all types of weatherstripping, porous and non-porous surfaces and general purpose bonding. Typical applications include bonding weatherstripping, insulation, rubber and trim to wood and metal.

TYPICAL PROPERTIES

Specific Gravity @ 25 °C	0.88
Flash Point - See MSDS	
Viscosity, Brookfield - RV, 25 °C, mPa·s (cP):	
Spindle 4, speed 20 rpm	6,000 to 10,000 ^{LMS}
Solids/Non-Volatile Content, %	30 to 34 ^{LMS}
Weight Per Gallon, lbs/gal	7.01 to 8.56 ^{LMS}

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

Directions for use

1. Clean surfaces thoroughly. Use abrasives to remove any powdery mold release from new weatherstripping.
2. Apply a thin, even film to both surfaces.

3. Allow to dry tacky (3 to 4 minutes).
4. Bond the two surfaces together and apply enough pressure to produce uniform contact.
5. **NOTE:** The early strength of LOCTITE® Contact Adhesive is enough to hold most parts together. However, maximum strength is obtained after the adhesive is completely dry. Aging of the bond and exposure to moderate heat increases strength.

Loctite Material Specification^{LMS}

LMS dated March 30, 1998. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons

against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0